

PERCENTAGE OF ASBESTOS (WEIGHT)

<u>ACOUSTICAL PLASTERS PRODUCTS</u>	<u>DATE</u>	<u>PERCENT ASBESTOS</u>
SABINITE "TF"	No Change	4.90%
SABINITE "B"	04/18/33	2.00%
	11/03/33	4.00%
SABINITE 38 (HYDRAULIC)	11/10/30	2.40%
	04/18/32	3.00%
	01/13/37	2.00%
	07/12/39	3.00%
SABINITE ACOUSTICAL PLASTER	05/23/30	.98%
	01/01/31	2.50%
	06/29/32	2.00%
	05/03/40	4.00%
SABINITE "M" and SABINITE SPECIAL WHITE	10/18/40	4.00%
	01/23/48	6.30%
SABINITE "F"	02/27/44	4.00%
	07/28/50	3.00%
	07/28/50	4.00%
	09/18/52	3.00%
SABINITE "A" or SABINITE HYDROCAL	04/04/31	4.00%
	04/18/33	2.00%
	11/03/33	4.00%
HI-LITE ACOUSTICAL PLASTER	06/09/53	6.20%
	03/31/55	6.30%
AUDICOTE SPECIAL WHITE	09/15/55	8.25%
	08/24/56	7.62%
	10/31/56	7.60%
	12/14/56	8.00%
	03/27/57	7.70%
	12/02/57	6.95%
	12/02/57	22.50%
	03/10/58	7.10%
	03/27/58	6.95%
	04/04/58	22.50%
	05/16/58	16.89%
	05/29/58	17.09%
	05/29/58	16.89%
05/29/59	16.88%	



ACOUSTICAL PLASTERS
PRODUCTS

	<u>DATE</u>	<u>PERCENT ASBESTOS</u>
	05/29/59	16.93%
	12/06/60	8.33%
	07/14/61	8.46%
	07/06/62	7.63%
	08/07/62	7.65%
	02/05/64	7.64%
	08/11/64	7.63%
AUDICOTE SATIN WHITE	09/15/55	8.43%
	08/24/56	7.78%
	10/31/56	7.76%
	03/27/57	7.47%
	12/02/57	26.24%
	03/10/58	8.06%
	03/27/58	7.47%
	04/04/58	26.24%
	05/16/58	19.66%
	05/29/58	19.49%
	05/29/58	19.66%
	05/29/59	19.22%
	05/29/59	19.70%
	12/06/60	8.60%
	07/14/61	8.73%
	07/06/62	7.85%
	08/07/62	7.87%
	02/05/64	7.86%
	12/22/64	7.85%
RED TOP ACOUSTICAL PLASTER*	04/25/51	9.70%
*SPRAYDON STANDARD A	No Change	29.70%
*SPRAYDON STANDARD G	No Change	7.60%
*SPRAYDON POWERCOTE	No Change	30.00%

* SprayDon U. S. Gypsum manufactured this product pursuant to the specifications of Sprayon Research Corporation.

<u>TEXTURE PRODUCTS</u>	<u>DATE</u>	<u>PERCENT ASBESTOS</u>
PAC-TEX	1943	4.5
	1953	4.5 - 6.0
	1954	3.5

A-B TEX	1935	4.0
	1943	4.5
	1944	4.0
USG TEXTONE TEXTURE PAINT	1928	3.3 - 4.5
	1930	2.8 - 4.5
	1934	3.3 - 4.5
	1938	2.67 - 5.0
	1943	2.67 - 6.0
	1947	2.67 - 8.0
	1952	2.5 - 3.5
	1955	1.2 - 3.5
	1956	2.3 - 3.5
	1958	1.2 - 6.0
	1960	1.2 - 10.0
	1970	.5 - 10.0
	1971	.5 - 3.5
SPECIAL TEXTURE PAINT	No Change	3.0 - 4.0
SPRAY TEXTURE PAINT	No Change	1.5 - 2.5
IMPROVED SPRAY TEXTURE	No Change	1.5 - 2.5
MULTI-PURPOSE TEXTURE	No Change	6.0 - 10.0
SANDED COLORED TEXTURE PAINT	No Change	2.0 - 4.0
USG MULTI-PURPOSE TEXTURE PAINT	1954	1.0 - 1.4
	1964	6.0 - 10.0
USG TEXTURE PAINT	No Change	2.5
SPRAY TEXTURE PAINT	1966	Unknown
	1968	5.0
	1969	2.0
USG MULTI-PURPOSE SPECIAL WHITE	No Change	5.0
USG MULTI-PURPOSE	No Change	6.0 - 10.0
USG MULTI-PURPOSE	No Change	4.0
SPECIAL TEXTURE PAINT	1956	Unknown
USG MULTI-PURPOSE SPRAY TEXTURE	No Change	4.0

USG MULTI-PURPOSE SPRAY TEXTURE	1972 1973	Unknown 4.0
SPRAY TEXTURE	No Change	1.5 - 2.5
AB TEX TEXTURE PAINT	No Change	.5
AB TEX TEXTURE PAINT	No Change	1.2 - 1.6
USG TEXTURE	No Change	1.6 - 3.5
MULTI-PURPOSE	1971	Unknown
SPRAY TEXTURE PAINT WHITE	1969 1973	7.3 0.0
SPRAY TEXTURE PAINT	1958 1971	1.5 - 3.0 4.5 - 6.0
SPRAY TEXTURE PAINT	No Change	1.5 - 3.0
SIMULATED ACOUSTICAL SPRAY	No Change	8.0
SIMULATED ACOUSTICAL SPRAY	No Change	8.0
SPRAY TEXTURE	No Change	1.5 - 3.0
SPRAY TEXTURE	No Change	1.5 - 4.0
SIMULATED ACOUSTICAL SPRAY	No Change	8.0
SIMULATED ACOUSTICAL SPRAY	1961 1962	Unknown 8.0
AGGREGATED SPRAY TEXTURE	No Change	1.0
AGGREGATED SPRAY TEXTURE	1962 1963	1.0 .5 - 1.5
SIMULATED ACOUSTICAL SPRAY	No Change	2.0
"QT" SIMULATED ACOUSTICAL SPRAY	1964 1969 1971	2.0 5.0 4.4
IMPERIAL QT SPRAY	No Change	1.5
AGGREGATED SPRAY	No Change	2.8

IMPERIAL QT REGULAR VERMICULITE	No Change	2.0
SPRAY TEXTURE	No Change	5.0
SMOOTH HARD FINISH	No Change	1.0
IMPERIAL QT TEXTURE	No Change	2.0
USG SUPER HARD SPRAY	No Change	1.2
USG SPRAY TEXTURE	No Change	5.0
SPRAY TEXTURE FINISH	No Change	.1
USG TEXTURE XII	No Change	3.0
USG SPRAY TEXTURE	No Change	5.0
USG TEXTURE XII SUPER VINYL	1971 1972	3.0 Unknown
USG SPRAY TEXTURE FINISH	1971 1974	4.0 5.0
SHEETROCK SMOOTHCOAT	No Change	1.0
USG EXTERIOR TEXTURE WALLBOARD FINISH	No Change	4.0
EXTRA HARD FINE IMPERIAL QT	No Change	1.0 - 3.0
SIMULATED ACOUSTICAL SPRAY TEXTURE	No Change	8.0
SIMULATED ACOUSTICAL SPRAY TEXTURE	No Change	8.0
IMPERIAL QT TEXTURE	No Change	4.0
SIMULATED ACOUSTICAL SPRAY	No Change	6.0
SIMULATED ACOUSTICAL SPRAY	No Change	6.5
SIMULATED ACOUSTICAL SPRAY	No Change	10.0

SIMULATED ACOUSTICAL SPRAY	No Change	8.0
SIMULATED ACOUSTICAL SPRAY	No Change	2.5 - 4.5
SIMULATED ACOUSTICAL SPRAY	No Change	2.5 - 3.5
SIMULATED ACOUSTICAL SPRAY	No Change	2.0
IMPERIAL QT	No Change	2.0
IMPERIAL QT	No Change	8.0
IMPERIAL QT	No Change	5.0
IMPERIAL QT	No Change	4.0
MULTI-PURPOSE TEXTURE	No Change	2.6
READY-MIXED SIMULATED ACOUSTICAL SPRAY	1966	Unknown
IMPERIAL QT	1966	4.0
IMPERIAL QT	1966	.94 - 1.0
IMPERIAL QT	1966	2.0 - 3.0
IMPERIAL QT	1966	3.0
IMPERIAL QT Polystrene	1966	6.0
SHEETROCK RADIANT HEAT SIMULATED ACOUSTICAL SPRAY	1966	6.0
SHEETROCK SIMULATED ACOUSTICAL SPRAY	1966	2.0
SHEETROCK SIMULATED ACOUSTICAL SPRAY	1966	3.5
AGGREGATED SPRAY TEXTURE	1966	5.0
IMPERIAL QT REGULAR	1967	Unknown
IMPERIAL QT REGULAR NC-4	1967	8.0
	1968	6.0

IMPERIAL QT	No Change	2.0
USG SPRAY TEXTURE FINISH	1965	.5
USG SPRAY TEXTURE FINISH	1965	.5
XH WHITE	1968	.5 - 1.5
AGGREGATED SPRAY TEXTURE	No Change	1.0
IMPERIAL QT	No Change	2.0
IMPERIAL QT	No Change	4.0
IMPERIAL QT COARSE VERMICULITE	No Change	2.0
IMPERIAL QT COARSE VERMICULITE	1970	5.1
	1971	6.1
USG SPRAY TEXTURE R	No Change	1.5
USG CONCRETE CEILING TEXTURE	No Change	6.0
TEXTONE TEXTURE FINISH	1944	2.5 - 4.5
	1967	3.5 - 5.5
	1972	2.5 - 4.5

Miscellaneous Specialty Plasters - Generally less than 1%

Fireproofing Plasters

Firecode V	Approximately 12%
Firecode V Type D	Approximately 12%

Ceiling Tile

Acoustone 120*	Approximately 3%
Acoustone 180	Approximately 3%

Texture Products - Approximately 3 - 5 %. Investigation continues as to individual texture products.

Paste Spackling Putty - Approximately 3%

Pipecoverings - Approximately 30 - 91%

*Not all formulations contained asbestos.

Ans to Inters. Consultations 1/24/92

Joint Compounds - Approximately 3 - 5%

Rigid Block Insulation - Approximately 10 - 21%

Mortar - Less than 1%

Siding Shingles - Approximately 12 - 15%

Roofing Shingles - Approximately 0.6 - 1%

Variation in asbestos content is usually reflective of formula changes relative to working properties.